

TECHNICAL DATA SHEET CURELAC ULTRAVIOLET GLOSS PRIMER COATING

PRODUCT LINE

10 Y 1000-KL ULTRAVIOLET GLOSS PRIMER COATING

APPLICATION

10 Y 1000-KL is an epoxy based overprint varnish. It is 100 % reactive and contains no solvents. This product has been designed as a flexible and recoatable coating. This coating can be utilized in blanket/roller, flexographic and dampener applications.

SPECIAL CHARACTERISTICS

- Recoatable
- Glueable
- Stampable
- High gloss
- Flexibility

PROPERTIES

RUB RESISTANCE: 200 RUBS/4LB.

GLOSS @ 60°: 90 PLUS

CURE RATE: 150 FPM/300 WATT

VISCOSITY: 170 - 200 CPS

ADHESION: EXCELLENT

SOLIDS: 100 %

PACKAGING

Plastic Kits	18.16 kgs.	40 lbs.
Drums	204.3 kgs.	450 lbs.